

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
28 December 2000 (28.12.2000)

PCT

(10) International Publication Number
WO 00/78820 A1

- (51) International Patent Classification⁷: C08F 4/658, (IT). BRITA, Diego [IT/IT]; Via Mulinetto, 63, I-44100 Ferrara (IT).
10/00
- (21) International Application Number: PCT/EP00/05349 (74) Agents: COLUCCI, Giuseppe; Montell Italia S.p.A., Intellectual Property, P.le G. Donegani, 12, I-44100 Ferrara et al. (IT).
- (22) International Filing Date: 8 June 2000 (08.06.2000)
- (25) Filing Language: English (81) Designated States (*national*): AU, BR, CA, CN, HU, IL, IN, JP, KR, MX, RU, SG, US, ZA.
- (26) Publication Language: English (84) Designated States (*regional*): European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).
- (30) Priority Data: 99201969.5 18 June 1999 (18.06.1999) EP
Published:
— With international search report.
— Before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments.
- (71) Applicant (*for all designated States except US*): BASSELL TECHNOLOGY COMPANY B.V. [NL/NL]; Hoeksteen 66, NL-2132 MS Hoofddorp (NL).
- (72) Inventors; and
(75) Inventors/Applicants (*for US only*): SACCHETTI, Mario [IT/IT]; Viale Krasnodar, 138, I-44100 Ferrara
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*



WO 00/78820 A1

(54) Title: CATALYST COMPONENTS FOR THE POLYMERIZATION OF OLEFINS AND CATALYSTS THEREFROM OBTAINED

(57) Abstract: The invention relates to catalyst components, suitable for the preparation of homopolymers and copolymers of ethylene having a broad molecular weight distribution (MWD), which comprise Ti, Mg, Cl, and are characterized by the following properties: surface area, determined by BET method, of lower than 100 m²/g, a total porosity, measured by the mercury method, of higher than 0.25 cm³/g, a pore radius distribution such that at least 45% of the total porosity is due to pores with radius up to 0.1 µm.